



MICROCOPY RESOLUTION TEST CHART NATIONAL BUREAU OF STANDARDS-1963-A



Semianrual Report

Switchable Zero Order Diffraction Gratings as Light Valves

Office of Naval Research Contract N00014-82-K-0522

covering the period 1 July 1982 - 31 December 1982

Submitted by John Melngailis



December 29, 1982

This document has been approved for public release and sale; its distribution is unlimited.

MASSACHUSETTS INSTITUTE OF TECHNOLOGY
Research Laboratory of Electronics
Cambridge, Massachusetts 02139

83 01 06 **013**

Introduction

The goal of this project is to build a light valve based on a switchable zero order diffraction grating. The grating is made switchable by fabricating it on two facing surfaces and then displacing one surface with respect to the other by half of one period. One way of producing the displacement is to use the strong piezoelectric properties of polyvinylidine fluoride (PVF). An alternate scheme using electrostatic forces is also being investigated. < Ultimately the light switches need to be mass producible, inexpensive, and capable of being fabricated into matrix addressable arrays. If the arrays are made with 525 by 700 elements, they could be used as flat back lighted TV screens. Smaller arrays might be useful for simpler displays. Another, potentially important use of the arrays would be in optical signal processing to convert electronic information into spatial light modulation.

Progress

A) Optical Properties:

So far our efforts have been focused on building a single working light valve element. To understand the optical properties of the bigrates (two facing gratings which constitute the light valve) some gratings of 3.8µm period where fabricated in quartz and tested in a spectrometer. Their transmission properties showed the expected behavior. Single gratings varied as a function of wavelength from 5% transmitting to 85% transmitting. When the gratings were put face to face to form a bigrate, the change from 4% transmission to 50% transmission could be observed. However, because the original mask was made

on a pattern generator, rather than holographically, the bigrate had a patchwork appearance. This is due to the stitching error in the pattern generator, i.e., each line in the grating is exposed in segments.

A) PVF₂ Properties and Fabrication:

Since strong piezoelectricity and light transmission is combined in one material in PVF_2 , this is the material we expect to use to fabricate the bigrates. PVF, samples have been obtained, techniques for applying metal have been developed, and lateral motion produced by applying a voltage have been observed. The piezoelectric coefficient d31, which determines the amounts of motion per applied electric field, has been measured. Sufficient motion to operate a bigrate can be obtained. A technique for producing a sinusoidal grating (used for black-white contrast) of 1.5µm period in nickel has been developed. It consists of holographically exposing and developing a sinusoidal profile grating in photoresist, plating thick nickel over it and then dissolving the resist. The resulting nickel template has been used to emboss PVF, at 20,000 psi. The gratings thus embossed appear to be stable, i.e., they do not relax. PVF, was found to be 90% transmitting in the visible spectrum and its index of refraction was measured to be 1.46.

A very rudimentary bigrate has been successfully demonstrated by attaching a PVF₂ strip with metal on two faces to one of two facing quartz gratings. Applying a voltage to the PVF₂ caused the grating to translate and to switch the optical transmission of

the bigrate. Our next immediate goal is to build this same structure entirely in PVF₂ using the embossing technique described above.

Our ability to emboss PVF₂ and to produce motion in the same material indicates inexpensive mass production may be possible.

C) Electrostatic Motion:

The electrostatic motion scheme may involve somewhat more complicated fabrication but may present advantages of guaranteed alignment and large flexibility in choice of materials. In this scheme interdigitated electrodes which run parallel to the gratings are fabricated on both facing elements and covered with a thin insulating film. Changing the sign of the voltage on the electrodes causes alternate attraction and repulsion and produces a relative movement of the elements. Simple calculations indicate that the forces are large enough to produce the desired motion. A set of masks with appropriate interdigital electrodes has been designed and fabricated in order to demonstrate this method of producing micromotion.

Conclusions

At this halfway point in the research program we have quined a good understanding of the optical principles of the bigrate, developed fabrication techniques for PVF₂, built a rudimentary electrically switchable light valve, and begun investigation of electrostatic motion. The participants in the project look forward with enthusiasm to the challenges ahead.

Fiscal Status

For the current year (July 1, 1982 - June 30, 1983) \$85,000 has been spent and committed out of the \$120,000 appropriated by DARPA.

DISTRIBUTION LIST

	DODAAD Code	<u> </u>
Leader, Information Sciences Office of Naval Research 800 North Quincy Street Arlington, Virginia 22217	N00014	(1)
Administrative Contracting Officer E19-628 Massachusetts Institute of Technology Cambridge, Massachusetts 02139	N66017	(1)
Director Naval Research Laboratory Attn: Code 2627 Washington, D.C. 20375	N00173	(6)
Defense Technical Infromation Center Bldg. 5, Cameron Station Alexandria, Virginia 22314	S47031	(12)
Office of Naval Research Eastern/Central Regional Office Bldg. 114, Sec. D 666 Summer Street Boston, Massachusetts 02210	N62879	(1)



